Product Data Sheet 1/2



# Q1<sup>®</sup> Pre Taped Washi Film

Pre-taped with Q1® Precision Line Masking Tape, this electrostatically treated masking film prevents over-spray flaking and drips, which means you can re-coat and clean up with complete confidence during any paint application. Ideal for quickly and easily masking both large and small surfaces whilst creating precise razor-sharp lines, this film is available in a variety of sizes, including; 550mm x 33m which is perfect for windowsills and skirting boards, a 1400m x 33m option for windows and kitchen cupboards and larger 2100mm x 20m or 2700mm x 16m for doors, walls and cabinetry. It's suitable for both indoor and outdoor use and is removable without a trace of adhesive residue for up to six months after use (indoor only).



# Features & Benefits

- Different dimensions for covering both small and large surfaces
- Pre-taped with Q1® Precision Line Masking Tape for razor sharp lines
- Suitable for indoor and outdoor use
- Quick and fast masking
- Unfolds easily and sticks well to surface

## Available Colour

Tape: Sun Yellow | Film: Clear

# **Product Reference**

Part#	Size	Pcs/ Case
Q1WMF550	550 mm x 33 m	40rolls/ box
Q1WMF1400	1400 mm x 33 m	20rolls/ box
Q1WMF2100	2100 mm x 20 m	20rolls/ box
Q1WMF2700	2700 mm x1 6 m	20rolls/ box

## **Technical Data Sheet**

Characteristics	Unit	Value	Test method
Таре			
Total Weight	g/m²	82	ISO 536
Total Thickness	mm	0.092	Internal
Adhesion to steel plate	N/cm	1.4	AFERA 5001/PSTC 101
Tensile strenght	N/cm	30	AFERA 5004/PSTC 131
Elongation at break	%	3.5	AFERA 5004/PSTC 131
UV light resistance	Hours	340	Atlas Suntest XLS+ (II)
HDPE Film			
Total Thickness	Micron	10	Internal
Density	g/cm³	0.949-0.957	ISO 1183
Yield stress	MPa	24	ISO 527
Tensile strenght	MPa	35	ISO 527
Heat distortion	°C	75	ISO 306
Heat break	°C	< -80	ASTM D 1709
Shore D Hardness		60	ISO 868

21/02/2020 / Rev. 01\_23\_05.2022

#### **Additional Information**

### Storage & Handling

Q1® Premium Masking Solutions must be stored in a dry location, protected from direct sunlight exposure and from freezing. Storage temperatures should be as close as possible to room temperature; suggested storage temperature should range from 59°F / 15°C to 77°F / 25°C with max. relative humidity of 50%. Do not store tapes and related products in the paint booth during bake cycles.

Make sure the surface you wish to place the tape on is cleaned, dried and free from oil and dust. It is suggested not to apply the tape with temperatures lower than  $50^{\circ}$ F /  $10^{\circ}$ C. With a storage temperature lower than  $50^{\circ}$ F /  $10^{\circ}$ C, it is always suggested temperature reconditioning of the tape at room temperature ( $79^{\circ}$ F /  $15^{\circ}$ C -  $59^{\circ}$ F /  $25^{\circ}$ C) before its use. We always recommend testing material in relation to the required applications.

### Shelf life from date of manufacture

No yellowing and < 10% loss in performance at 73.4°F / 23 °C, 50″% humidity is considered 12 months Q1® Premium Masking Solutions does not take responsibility for the defective material if is not stored and used in accordance with the conditions listed above.

#### **Technical Information Disclaimer**

The technical information, suggestions and other statements contained in this documents have been compiled for your guidance and usage. Information is based on experience and tests that Q1® Premium Masking Solutions believe are reliable. The accuracy or completeness of such information is not guaranteed. Q1® Premium Masking Solutions has no control about conditions in which products are used, stores or handles. The above information doesn't constitute a warranty.

#### **Product Use**

Q1® would advise that there are many factors beyond Q1® control but within the users knowledge that can affect the use and performance of Q1® products. Q1® remind the user of the products to make sure that its range is used as per the instructions printed above. It is the users sole responsibility to determine that all preparation has been correctly carried out and that the working conditions are as per Q1® literature.